

CB MINERALS

2 Madison Ave. #211

Larchmont, NY 10538

Tel: 914-777-3330 Fax: 914-777-3035

WEBSITE: www.cbminerals.com

E-Mail: info@cbminerals.com

INDUSTRIAL MINERALS SINCE 1897

BENTONITE SEMI-DRIED CRUDE

This is a pure, sodium Bentonites produced as a Semi-Dried form for the ease of bulk transportation and processing.

CHEMICAL ANALYSIS:

SiO ₂	60 - 62 %
Al ₂ O ₃	18 - 20 %
Fe ₂ O ₃	3.5 - 4 %
Na ₂ O	2.3 %
TiO ₂	0.2 %
CaO	0.4 %
MgO	1.7 %
K ₂ O	0.1 %
Other	0.07%

PHYSICAL ANALYSIS:

Color	Light Gray
LOI	4.37%
Moisture	11.5 - 14.5 %
Apparent Density	0.95 - 1.10
Spec. Gravity	2.55
Cation Exchange Capacity	70-90 CEC meg (100 gr)
Swell	18-22 cc/2 gr.
Size	100% passing 5 cm.

E.P. TOXICITY ANALYSIS:

	E.P.A. Standard ppm	Typical Analysis ppm
Arsenic	5.0	<0.1
Barium	100.0	0.5
Cadmium	1.0	<0.05
Chromium	5.0	<0.1
Lead	5.0	<0.1
Mercury	0.2	<0.02
Selenium	1.0	<0.05

PACKING:

Bulk

ORIGIN:

U.S.A.