

CHARLES B. CHRYSTAL CO., INC

689 Mamaroneck Ave.
Mamaroneck, NY 10543
Tel: 914 777 3330 Fax: 914 777 3035
WEB SITE: www.cbcrystal.com
E-Mail: info@cbcrystal.com
INDUSTRIAL MINERALS SINCE 1897

RHASSOUL CLAY

A yellow reddish clay ideal for facisl masks, clay baths, soaps, etc. This clay is treated to be free of bacteria and suitable for cosmetic use.

CHEMICAL ANALYSIS:

Silicone Dioxide	(SiO ₂)	65.0 %
Aluminum Oxide	(Al ₂ O ₃)	17.1
Titanium Dioxide	(TiO ₂)	1.2
Iron Oxide	(Fe ₂ O ₃)	6.7
Calcium Oxide	(CaO)	0.3
Magnesium Oxide	(MgO)	1.1
Potassium Oxide	(K ₂ O)	2.8
Sodium Oxide	(Na ₂ O)	0.6
Carbon	(%C)	0.2

PHYSICAL ANALYSIS:

Loss on Ignition	(L.O.I.)	5.2 %
Particle Size as % Finer than		
20 Micron		75%
10 Micron		64
5 Micron		51
2 Micron		37
1 Micron		28
0.5 Micron		20
Specific Gravity		2.6

PACKING:

100 lb Drum

BACTERIA:

Irradiated - 100 TPC Max, Typical Zero

ORIGIN:

USA