

CHARLES B. CHRYSTAL CO., INC

689 Mamaroneck Ave.

Mamaroneck, NY 10543

Tel: 914 777 3330 Fax: 914 777 3035

WEB SITE: www.cbchrystal.com

E-Mail: info@cbchrystal.com

INDUSTRIAL MINERALS SINCE 1897

WHITE PAPER COATING CLAY

This is very white, Calcined Kaolin. It is used for filling and coating application in newsprint, coated ground wood, coated and uncoated free sheets, and top white linerboard. It can reduce the TiO₂ demand.

| Physical specification | Typical Value |
|--------------------------|------------------|
| Brightness | 92.5 GE |
| Finer than 2 micron | 94% |
| PH | 6.5 |
| Residue on 325 | 0.005 |
| Slurry | up to 50% solids |
| LOI | 0.5% |
| Einlehner abrasion 100 K | 13 |

Advantages:

- Reduces TiO₂
- Improved print appearance and strike through
- Improved brightness
- Improved ocapacity
- Improved printability

Pack: Super sacks, pulpable bags, and slurry

Origin: USA